



Solvent Cemented Pipe Joints Initial Set Schedule, Cure Schedule And Cement Usage Table

The following are basic guidelines and may require adjustment according to application or installation conditions. Certain specialty cements, such as FlameGuard® FS-5, may have different instructions for specific application conditions. Consult appropriate installation instructions for details.

INITIAL SET SCHEDULE: The Initial set schedule is the necessary waiting period before handling newly assembled joints. After initial set, the joint will withstand the stress of a normal installation. In damp or humid weather allow 50% more set time.

AVERAGE INITIAL SET SCHEDULE FOR SPEARS® PVC/CPVC SOLVENT CEMENTS

Temperature Range	Pipe Sizes 1/2" to 1-1/4"	Pipe Sizes 1-1/2" to 2"	Pipe Sizes 2-1/2" to 8"	Pipe Sizes 10" to 15"	Pipe Sizes 15"+
60°-100°F/16°-38°C	2 minutes	5 minutes	30 minutes	2 hours	4 hours
40°-60°F/5°-16°C	5 minutes	10 minutes	2 hours	8 hours	16 hours
0°-40°F/-18°-5°C	10 minutes	15 minutes	12 hours	24 hours	48 hours

JOINT CURE SCHEDULE: The Joint cure schedule is the necessary waiting period before pressurizing newly assembled joints. Follow the schedule carefully. In damp or humid weather or chemical applications, allow a minimum of 50% more cure time.

AVERAGE JOINT CURE SCHEDULE FOR SPEARS® PVC/CPVC SOLVENT CEMENTS

Relative Humidity 60% or Less	Cure Time Pipe Sizes 1/2" to 1-1/4"		Cure Time Pipe Sizes 1-1/2" to 2"		Cure Time Pipe Sizes 2-1/2" to 8"		Cure Time Pipe Sizes 10" to 15"	Cure Time Pipe Sizes 15"+
	Up to 160 psi	Above 160 to 370 psi	Up to 160 psi	Above 160 to 315 psi	Up to 160 psi	Above 160 to 315 psi	Up to 100 psi	Up to 100 psi
60°-100°F/16°-38°C	15 min	6 hrs	30 min	12 hrs	1-1/2 hrs	24 hrs	48 hrs	72 hrs
40°-60°F/5°-16°C	20 min	12 hrs	45 min	24 hrs	4 hrs	48 hrs	96 hrs	6 days
0°-40°F/-18°-5°C	30 min	48 hrs	1 hour	96 hrs	72 hrs	8 days	8 days	14 days

AVERAGE NUMBER OF JOINTS PER QUART OF SPEARS® CEMENT

Pipe Diameter	1/2"	3/4"	1"	1-1/2"	2"	3"	4"	6"	8"	10"	12"	15"	18"
Number of Joints	300	200	125	90	60	40	30	10	5	2-3	1-2	3/4	1/2

NOMINAL INCH AND CORRESPONDING NOMINAL MILLIMETER PIPE SIZES

in.	1/2"	3/4"	1"	1-1/4"	1-1/2"	2"	2-1/2"	3"	4"	6"	8"	10"	12"	14"	18"	24"	30"
mm.	20	25	32	40	50	63	75	90	110	160	200	250	315	355	450	600	800

SPEARS® APPLICATOR SELECTION GUIDE

For proper solvent cement welding of pipe and fittings, the cement applicator must be no less than half the size of the pipe

DAUBERS	Pipe Diameters							
	1/4"	1/2"	3/4"	1"	1-1/4"	1-1/2"	2"	3"
3/8" Dauber	•	•	•					
1/2" Dauber			•	•				
5/8" Dauber				•	•			
3/4" Dauber					•	•		
1-1/4" Dauber							•	•

ROLLERS & SWABS	SIZE	FOR PIPE DIAMETERS
3020	3" Roller	3" - 6"
6020	4" Roller	3" - 8"
7020	7" Roller	6" +
5520	4" Roller	6" +
6520	6" Roller	6" +
4020	4" Swab	6" +
5020	4" Swab	3" - 8"
4520	4" Swab	6" +

PRODUCT SHELF LIFE

Spears® Products	Shelf Life	Spears® Products	Shelf Life
Primers / Cleaners	3 years	CPVC Solvent Cement	2 years
PVC Solvent Cement	3 years	ABS Solvent Cement	3 years

Prices subject to change without notice. Possession of this price schedule shall not be construed as an offer to sell the products listed. Product drawing(s) & photo(s) are representative and may not fully reflect product configuration.

NOT FOR DISTRIBUTION OF COMPRESSED AIR OR GAS

Progressive Products from Spears® Innovation & Technology